

TABULKA VII
 Tenze nasycených par [79KUB],[84ALC] (data pro As₄ [75RAU])

Látka	log p°(Pa) = A + B/T + C.log T			Obor teplot (K)
	A	B	C	
Al(l)	10,917	-16211		930 - 1800
As ₄ (s)	13,527	-7591,5		720 - 1100
As ₄ (l)	8,702	-2332,2		1050 - 1400
AsCl ₃ (l)	26,885	-2660	-5,83	260 - 410
As ₄ O ₆ (s)	13,035	-5282		370 - 580
Ca(l)	15,694	-9103	-1,71	1110 - 1780
CaF ₂ (s1)	29,535	-23600	-4,525	298 - 1430
CaF ₂ (s2)	29,355	-23350	-4,525	1420 - 1700
CaF ₂ (l)	28,435	-21800		1690 - 2790
Cd(hcp)	10,945	-5799		298 - 600
Cd(l)	10,248	-5392		580 - 650
Fe(CO) ₅ (l)	10,545	-2075		298 - 390
Ga(l)	11,760	-13984	-0,3413	300 - 1600
GaCl ₃ (l)	31,265	-4886	-6,44	298 - 580
Hg(l)	10,122	-3190		298 - 400
I(s)	18,386	-3518	-2,02	298 - 390
In(l)	10,380	-12276		430 - 1500
Na(l)	13,406	-5634	-1,1748	370 - 800
Ni(CO) ₄ (l)	9,855	-1530		298 - 340
Pb(l)	9,917	-9701		600 - 1200
Sb ₄ O ₆ (cub)	14,320	-10360		740 - 840
Sb ₄ O ₆ (ort)	13,437	-9625		740 - 920
Sb ₄ O ₆ (l)	7,262	-3900		929 - 1073
Si(l)	12,905	-20900	-0,565	1680 - 3550
SiCl ₄ (l)	9,765	-1572		270 - 340
Sn(s)	11,042	-15710		298 - 510
Sn(l)	10,268	-15332		500 - 1850
TiCl ₄ (l)	27,254	-2919	-5,788	298 - 410

Látka	$\log p^\circ(\text{Pa}) = A + B/T + C \cdot \log T$			Obor teplot (K)
	A	B	C	
Zn(s)	11,108	-6776		298 - 700
Zn(l)	10,384	-6286		690 - 750